COMMISSION REGULATION (EEC) No 2310/80

of 3 September 1980

laying down for the 1980/81 and 1981/82 wine-growing years conditions of use of ion exchange resins and detailed implementing rules for the preparation of rectified concentrated grape must

THE COMMISSION OF THE EUROPEAN COMMUNITIES,

Having regard to the Treaty establishing the European Economic Community,

Having regard to Council Regulation (EEC) No 337/79 of 5 February 1979 on the common organization of the market in wine (1), as last amended by Regulation (EEC) No 1990/80 (2), and in particular Article 46 (6) thereof,

Whereas the Council recently authorized the preparation and use of rectified concentrated grape must; whereas point 1 a (h) of Annex III to Regulation (EEC) No 337/79 permits the use of ion exchange resins for the preparation of this product, under conditions to be laid down; whereas the conditions of use of such resins must therefore be laid down;

Whereas in so doing account must be taken of the provisions already adopted at Community level by Council Directive 76/893/EEC of 23 November 1976 on the approximation of the laws of the Member States relating to materials and articles intended to come into contact with foodstuffs (3), and of Community and national provisions adopted in implementation of the said Directive;

Whereas the authorized treatments must be such as to ensure that the product obtained presents no hazard to health; whereas provision must therefore be made for the inspection of the substances used and for the methods of analysis to be used in the course of such inspections;

Whereas studies concerning supervision of the use of ion exchange resins are in progress at Community level; whereas, pending the results of this work, the application of this Regulation should be limited to two wine-growing years;

Whereas the measures provided for in this Regulation are in accordance with the opinion of the Management Committee for Wine,

HAS ADOPTED THIS REGULATION:

Article 1

Ion exchange resins may be used for the preparation of rectified concentrated grape must only under the supervision of an oenologist or technician, and in installations approved by the authorities of the Member State on whose territory the resins are used. Such authorities shall lay down the duties and responsibility incumbent on approved oenologists and technicians.

Article 2

The ion exchange resins which may be used are styrene and divinylbenzene copolymers containing sulphonic acid or ammonium groups. They must comply with Directive 76/893/EEC and Community and national provisions adopted in implementation thereof. In addition, when tested by the method of analysis laid down in the Annex, they must not lose more than 1 mg/l of organic matter into any of the solvents listed.

Their regeneration must be effected with substances permitted for use in the preparation of foodstuffs.

Article 3

This Regulation shall enter into force on the third day following its publication in the *Official Journal of the European Communities.*

It shall apply from 1 September 1980 to 31 August 1982.

This Regulation shall be binding in its entirety and directly applicable in all Member States.

Done at Brussels, 3 September 1980.

For the Commission

Finn GUNDELACH

Vice-President

(1) OJ No L 54, 5. 3. 1979, p. 1.
(2) OJ No L 195, 29. 7. 1980, p. 6.
(3) OJ No L 340, 9. 12. 1976, p. 19.

ANNEX

THE USA METHOD FOR ORGANIC MATTER IN ION EXCHANGE RESINS

DETERMINATION OF THE LOSS OF ORGANIC MATTER FROM ION EXCHANGE RESINS

1. Scope and field of application

The method determines the loss of organic matter from ion exchange resins.

2. Definition

The loss of organic matter from ion exchange resins :

The loss of organic matter is determined by the method specified.

3. Principle

Extracting solvents are passed through prepared resins and the weight of organic matter extracted is determined gravimetrically.

4. Reagents

All reagents should be of analytical quality grade.

Extracting solvents :

4.1. Distilled water or de-ionised water of equivalent purity.

4.2. Ethanol, 15 % v/v. Prepare by mixing 15 volumes of absolute ethanol with 85 volumes of water (4.1).

4.3. Acetic acid, 5 % m/m. Prepare by mixing 5 parts of weight glacial acetic acid with 95 parts by weight of water (4.1).

5. Apparatus

5.1. Ion exchange chromatograph columns.

5.2. Measuring cylinders, capacity 2 l.

5.3. Evaporating dishes, capable of withstanding a muffle furnace at 850 °C.

5.4. Drying oven, thermostatically controlled at 105 + or — 2 °C.

5.5. Muffle furnace, thermostatically controlled at 850 + or — 25 °C.

5.6. Analytical balance, accurate to 0·1 mg.
mg.

5.7. Evaporator, hot plate or infra-red evaporator.

6. Procedure

6.1. Add to each of three separate ion exchange chromatography columns (5.1) 50 ml of the ion exchange resin to be tested, having been washed and treated in accordance with the manufacturers direction for preparing them for use with food.

6.2. Pass the three extracting solvents (4.1, 4.2 and 4.3) separately, through the prepared columns (6.1) at a flow rate of 350 to 450 ml/h. Discard the first litre of eluate in each case and collect the next two litres in measuring cylinders (5.2).

6.3. Evaporate the three eluates over a hot plate or infra-red evaporator (5.7) in separate evaporating dishes (5.3) which have been previously cleaned and weighted (m0). Place the dishes in an oven (5.4) and dry to constant weight (m1).

6.4. After recording the constant weight (6.3), place the evaporating dish in the muffle furnace (5.5) ash to constant weight (m2).

6.5. Calculate the organic matter extracted (7.1). If the result is greater than 1 mg/l, carry out a blank test on the reagents and recalculate the content of organic matter extracted.

The blank test should be carried out by repeating sections 6.3 and 6.4 but using two litres of the extracting solvent, to give weights of m3 and m4 in sections 6.3 and 6.4 respectively.

7. Expression of results

7.1. Formula and calculation of results.
The organic matter extracted from ion exchange resins, in mg/l, is given by:

$$500\ (m1 - m2)$$

where m1 and m2 are in g.

The correct organic matter extracted from ion exchange resins, in mg/l, is given by:

$$500\ (m1 - m2 - m3 + m4)$$

where m1, m2, m3 and m4 are in g.

7.2. The difference in the results between two parallel determinations carried out on the same sample shall not exceed 0·2 mg/l.